

Ratings

Voltage: 300 V
 Temperature: 80 °C
 Flammability: VW-1, FT1

Conductor

Conductor count: 5
 Gauge: 24 AWG, 0.22 mm²
 Material: tinned copper strands
 Stranding: $\phi 0.16 \times 11$
 Resistance at 20 °C: 95 ohm/km maximum

Insulator

Material: SRPVC, 80 °C
 Color: black, white, red, yellow, blue
 Outer diameter: $\phi 1.2 \pm 0.10$ mm
 Thickness: 0.23 mm minimum average
 Style: UL 1061

Outer jacket

Material: PVC, 80 °C
 Color: white
 Diameter: $\phi 4.6 \pm 0.30$ mm
 Thickness: 0.76 mm minimum average



Wire marking: E339579 UL AWM STYLE 2464 24AWG 80°C 300V VW-1 --- cUL AWM I A 80°C 300V FT1 TENSILITY

Tests

Tensile strength: 1.05 kgf/mm²
 After aging at 113 ±2 °C for 7 days:
 Minimum tensile strength 70 % original
 Minimum elongation 65 % original
 Flexibility: no observed cracking
 Heat shock: 121 ±1 °C /1 hour, no observed degradation
 Deformation: 121 ±1 °C /1hour, ≤ 50 %
 Cold bend: -10 ±2 °C /1 hour, no observed cracking
 Dielectric: 2000 Vac for 1 minute without breakdown

Use:

Internal wiring or external interconnection of electronic equipment



REVISION	DATE	DESCRIPTION
A	10/13/2015	Initial release
A1	1/26/2016	Updated stranding

PREPARED:

VERIFIED:

DIMENSIONS ARE IN MILLIMETERS

TOLERANCES:
 X: ± 0.5 mm
 X.X: ± 0.3 mm
 X.XX: ± 0.05 mm

NOTES
 RoHS and REACH compliant

Function test: no open, no reversed polarity, no short circuit, no INT

Functionally equivalent components may be used

Drawing in third angle projected

DESCRIPTION:
 Wire, 5C TS, 24 AWG, UL2464, 300V, 80C, 4.6 mm, VW-1, PVC, white

TENSILITY

20802 Sockeye Place #130
 Bend, OR 97701 USA
 tel 541.323.3228 fax 541.323.4202
 800 877.670.7118 www.tensility.com

SIZE A	PART NUMBER 30-00502
-----------	-------------------------

SCALE: 1:1

SHEET 1 OF 1